



AMBANI ORGANICS PVT. LTD.

801, "351 – ICON", Andheri (E), Mumbai – 400069 ,India

Tele – 022 26833778 www.ambaniorganics.com

AOPL PS 504 Styrene Acrylic 50%

Chemical type	: Styrene Acrylic
Visual Appearance	: Milky white Viscous Emulsion
Solid content	: 50 +/- 1%
Viscosity @ 30 C Brookfield RVT Spindale No 4 RPM 10	: 6000 - 8000 c.Ps
pH	: 8 ~ 9
Free monomer content	: < 0.3%
MFFT	: 18°C ca
Properties	Forms a hard, tough, flexible & glossy film. Excellent wet scrub & abrasion resistance. Excellent pigment loading characteristics. Alkali resistant.
Recommended Applications	For use in superior quality exterior/interior emulsion paints with high sheen, textured coating & in construction chemicals.

ISO: 9001 : 2008 Certified

The above information is to the best of our knowledge true and accurate. Since the conditions that the products are used in cannot be handled or controlled by us we cannot guarantee the results and assume liability to damages incurred by using this product
Refer to M.S.D.S. for handling procedures.